



Flexiber Film AG60CWA

PRODUCT FEATURES

- Excellent scratch resistance
- Consistent gloss/antiglare surface
- Chemical and household cleaner resistance
- Excellent printable surface
- Dimensionally Stable

STRUCTURE



OPTICAL AND PHYSICAL PROPERTIES

| PROPERTY | | TEST METHOD | U/M | AG60CWA |
|---------------------------|----|-------------|---------|-----------|
| Total Light Transmittance | | ASTM D1003 | % | ≥ 90 |
| Haze | | ASTM D1003 | % | 53 ± 5 |
| Haze after screen ink | | ASTM D1003 | % | ≤ 15 |
| Clarity after screen ink | | ASTM D1003 | % | ≥ 90 |
| Pencil hardness | | ASTM D3363 | - | ≥ 2H |
| Tape adhesion | | ASTM D3002 | 100/100 | Pass |
| Heat Shrinkage | TD | 120°C 30min | % | TD: ≤ 0.1 |
| | MD | | % | MD: < 0.2 |

^{*} Technical data is based on sample measurement at KTI.

^{*} Ink tested: SERICOL UVIBOND UV383.